

certoplast 730 SE

Structure

Pure **aluminium foil** in combination with a special **rubber-based adhesive**, foil-protected

Properties

- high shear strength
- strong initial tack
- vapour tight
- flexible
- durable adhesion
- tearable by hand
- according to DIN 4102 part 1 B1
- Inspected by the MPA BS
- **ABP-Nr. P-3737/8823-MPA BS**

Colour

- aluminium

Application

certoplast 730 SE is suitable as a sealing tape for joint intersections of aluminium laminated dam-systems. It can be used for all applications with special demands concerning flame resistance according to DIN 4102 part 1 B1.

Technical data

| | value | dimension |
|-------------------------------------|----------------|------------------------|
| backing | pure aluminium | |
| aluminium foil | 0,030 | mm |
| adhesive | rubber-based | |
| tensile strength | ≥ 20,0 | N/cm |
| elongation | ≥ 5 | % |
| adhesion to steel | ≥ 8,0 | N/cm |
| temperature range (when applied) | -40 / +80 | °C |
| water vapour permeability | ≤ 1 | g/m ² * 24h |

Form of supply

| | value | dimension |
|----------|-------------------|-----------|
| width * | 50, 75, 100 ± 0,5 | mm |
| length * | 50, 100 ± 2% | m |
| core * | 76 | mm |

* other sizes upon request



Recommendations for use

Fix the tape to the desired surface immediately after removing the cover and press tightly. The best results are obtained at a working temperature between 20 and 24°C.

Remark: The surface to which the tape is to be fixed must be free of oil or other contaminants such as powder, dirt or release agents. The adhesive power can be affected if the substrates contain softeners.

These details are to the best of our knowledge, nevertheless without guarantee. The suitability for special applications should first be tested by the user. The given values are statistical averages

certoplast

Vorwerk Sohn GmbH
Technische Klebebänder
Müngstener Straße 100
D-42285 Wuppertal

Tel. +49(0)2 02-2 55 48-0
Fax. +49(0)202-2 55 48 48